



LETO 145

BREATHER MEMBRANE


WIND UPLIFT RESISTANCE

1-5

TAPED LAP

1-3

BATTENED LAP



TECHNICAL CHARACTERISTICS

Resistance to water penetration, class	w1
Water vapour transmission properties (sd), m	0.02
Tensile strength to EN12311-1 (MD), N/50mm	300
Tensile strength to EN12311-1 (CD), N/50mm	200
Nail tear resistance to EN12310-1 (MD), N/50mm	120
Nail tear resistance to EN12310-1 (CD), N/50mm	140
Flexibility at low temperature to EN1109:2013	-40°C
Reaction to fire, class	E
Weight, gsm	145



PERMAVENT

INNOVATIVE CONSTRUCTION PRODUCTS

n.cooper@permavent.co.uk +44 7917 864 200

11 Cumberland Drive, Granby Industrial Estate, Weymouth. DT4 9TB